

Am 2-28-05

Appl. Serial No.: 09/737,109
Filed: December 14, 2000
Group Art Unit: 1771
Examiner: A. Wachtel
Atty. Docket No.: 72545-37

21. (Original) The filter media composite of claim 1, wherein said chopped glass fibers have between about 55% and about 65% SiO₂ by weight.
22. (Original) The filter media composite of claim 21, wherein said chopped glass fibers have between about 59% and about 60% SiO₂ by weight.
23. (Original) The filter media composite of claim 1, wherein said chopped glass fibers have between about 10% and 15% Al₂O₃ by weight.
24. (Original) The filter media composite of claim 23, wherein said chopped glass fibers have about 13% Al₂O₃ by weight.
25. (Cancelled).
26. (Original) The filter media composite of claim ~~25~~⁷, wherein said chopped glass fibers have less than about 0.6% boron by weight.
27. (Original) The filter media composite of claim 1, wherein said chopped glass fibers have less than about 1% iron oxides by weight.
28. (Original) The filter media composite of claim 27, wherein said chopped glass fibers have less than about 0.5% iron oxides by weight.
29. (Original) The filter media composite of claim 1, wherein said chopped glass fibers have less than about 2% sodium oxide by weight.
30. (Original) The filter media composite of claim 29, wherein said chopped glass fibers have less than about 1.0% sodium oxide by weight.
31. (Original) The filter media composite of claim 1, wherein said chopped glass fibers have less than about 3.0% potassium oxide by weight.